



SBS

NILOSHEILD SBS

SBS Modified Bitumen Waterproofing Membrane

With Dual Reinforcement (Glassfiber & Nonwoven Polyester)

THE PRODUCT

NILOSHEILD SBS is an elastomeric waterproofing membrane manufactured in an advanced continuous calendaring process by saturating and coating two synthetic carriers (Glassfiber mat and nonwoven Polyester) with a waterproofing compound made of a special grade of bitumen, which is modified with SBS polymers. While the polymers SBS enhance the thermal, mechanical, and aging properties of the membrane compound, the mechanical characteristics of **NILOSHEILD SBS** are established by the dual synthetic carriers made of non-woven Polyester and fiberglass mat, which acts as the reinforcement that provides the membrane with the profound mechanical properties of the Polyester and the prominent dimensional stability of Glassfiber mat.

The upper surface of **NILOSHEILD SBS** is covered with an anti-adhesive finish material while the lower face is laminated with a thermo-fusible polyethylene film.

USES

NILOSHEILD SBS can be used for roofing & waterproofing applications with high dimensional stability requirements and subjected to movement, considerable mechanical stresses & moderate weathering conditions.

NILOSHEILD SBS is a multi-purpose waterproofing membrane particularly recommended in single or multi-layer systems for the following applications:

- Flat and sloped ballasted roofs.
- Underground structures waterproofing.
- Re-roofing works.
- Wet areas and mechanical rooms waterproofing.

NILOSHEILD SBS MINERAL is used for exposed applications or as a cap-sheet in a multi-layer system.

SURFACE FINISH

The lower surface of **NILOSHEILD SBS** is laminated with a Polyethylene film while the upper surface is covered with one of the following surface finish materials:

- Fine Sand **NILOSHEILD SBS– S/E**
- Polyethylene Film **NILOSHEILD SBS– E/E**
- Mineral Slate Chips **NILOSHEILD SBS MINERAL**
Or Special Granules

APPLICATION

NILOSHEILD SBS is usually applied by using a propane torch or a hot air generator as well as by mechanical fastening. It can also be applied using special adhesives in cold or hot applications. The substrate surface must be clean, dry, smooth, and free from any irregularities. According to the surface conditions, a coat of BituNil primer maybe required prior to the application of the membrane. **NILOSHEILD SBS** can be applied to the substrate fully bonded, semi bonded or loose laid, The method of adhesion to the substrate shall be decided according to the waterproofing system design. Side laps should be from 8-10 cm, while end laps should be from 12-15 cm. For more information on application refer to BituNil application guide.

STORAGE & HANDLING

NILOSHEILD SBS rolls should be kept in an upright position in a flat, properly ventilated and sheltered storage area.

STANDARD SUPPLY DATA & PALLETISING

Group 100	Group 105	Thickness *	Standard Roll Size	Rolls/ Pallet	
				Group 100	Group 105
300	305	3mm	1M x 10M	28	28
400	405	4mm	1M x 10M	23	23
*Thickness tolerance as per UEAtc. Directives for Group 100 and UEAtc. ± 5% for Group 105.					
Group 1000	Group 1005	Weight **	Standard Roll Size	Group 1000	Group 1005
3000	3005	3Kg/ sqm	1M x 10M	39	39
4000	4005	4 Kg/ sqm	1M x 10M	30	30
5000	5005	5 Kg/sqm	1M x 10M	23	25
**Weight tolerance as per UEAtc. Directives for Group 1000 and UEAtc. ± 5% for Group 1005.					

Loading Capacity: 20 pallets / Container

The above quantities are indicative only and may be subject to changes in order to comply with transport limitations according to the final destination of the product.

BituNil membranes are made of non-polluting substances, therefore are safe products during production, application and use.

NEILOSHEILD SBS

SBS Modified Bitumen Waterproofing Membranes With Dual Reinforcement.

Properties	Test	Unit	Test Method	Tolerance	NILOSHEILD SBS	
Dimensional Properties	Thickness	mm	EN-1849-1	± 5%	4	
	Weight (Mass Per Unit Area)	kg/m ²	EN-1849-1	± 10%	-	
	Determination Of Width	m	EN-1848-1	± 1%	1	
	Determination Of Length	m	EN-1848-1	± 1%	10	
	Straightness (Ortometry)	mm	EN-1848-1	-	± 10	
Compound Properties	Softening point (R&B)	° C	ASTM D- 36	Min.	110	
	Compound Elongation	%	UNI 8202/8	± 15%	900	
Membrane Properties	Mechanical properties	Tensile Strength - Longitudinal	N/50mm	EN-12311-1	± 20%	800
		Tensile Strength - Transverse	N/50mm	EN-12311-1	± 20%	500
		Elongation At Break - Longitudinal	%	EN-12311-1	±15	40
		Elongation At Break - Transverse	%	EN-12311-1	±15	45
		Tearing Strength - Longitudinal (Nail-Shank)	N	EN-12310-1	± 30%	200
		Tearing Strength - Transverse(Nail-Shank)	N	EN-12310-1	± 30%	250
		Tensile Tear Resistance - Longitudinal	N	ASTM D- 5147 . D 4073	± 30%	500
		Tensile Tear Resistance - Transverse	N	ASTM D- 5147 . D 4073	± 30%	375
		Resistance to Static Loading	Kg	EN 12730 Method A	Min.	15
	Dynamic Puncturing (Impact Resistance)	mm	EN 12691 Method B	Min.	500	
	Thermal Properties	Flow Resistance At Elevated Temperature	° C	EN-1110	Min.	90
		Flexibility At Low Temperature ⁽¹⁾	° C	EN-1109	-	-10 to -5
		Dimensional Stability	%	EN-1107-1	Max.	±0.3
		Water Impermeability- Watertightness at Low pressure	60 Kpa	EN-1928 Method A	-	Passed
		Water Impermeability- Watertightness at High pressure ⁽²⁾	Kpa	EN-1928 Method B	Min.	300
	Miscellaneous Properties	Water Absorption	%	ASTM D-5147	Max.	< 1
		Vapour Permeability	µ	EN 1931	-	40000
		Fatigue resistance on cracks	200 cycles	UNI 8202/13	-	-
			500 cycles		-	-
		Shear Resistance Of joints - Longitudinal	N/50mm	EN-12317-1	± 20%	800
		Shear Resistance Of joints - Transverse	N/50mm	EN-12317-1	± 20%	500
		Thermal Ageing in air (in oven 28 days at 70 °C)	-	UNI 8202 /26	-	Passed
		Ageing Due To Atmospheric Agents (U.V Test weathering)	-	ASTM G 53 UNI 8202/29	-	-
		Fatigue resistance at Joints	200 cycles	UNI 8202/32	-	-
			500 cycles		-	-
		Fire Classification - External Fire Performance	Class	EN 13501-5/ ENV 1187	-	F Roof
		Reaction to fire	Class	EN 13501-1	-	E
		Adhesion Of Granules	%	EN-12039	Max.	≤30
		Adhesion To Concrete (Torch Applied)	N/ 50mm	Pelage UEAtc	-	40
	Resistance to root penetration	-	EN-13948	-	NPD	
	Supply Data	weight	kg/m ²	-	-	3 to 6
		Thickness	mm	-	-	2 to 5
		Roll Length	M	-	-	10
Roll Width		M	-	-	1	
Surface finish (E: Polyethylene film S: Sand SL:Slates GR: Granule)						
Upper Surface Finish		-	-	-	-	S or E or SL or GR
Lower Surface Finish	-	-	-	-	S or E	

The declared average values represent the best performance achieved at the present state of our knowledge, BITUNIL S.A.E reserves the possibility to change, without warning, the technical characteristics in order to make the product more responding to the Application requirements. The choice of the type of membrane for the kind of use is at the purchaser's discretion .

Distributor:

Tolerances for the above values if not mentioned are according to the UEAtc directives.

- (1) Exact value depends on thickness of the product.
- (2) Deviating from the standard method , The assessment is made in 1 Hour test 4mm or 4.5Kg/m² products.



Nile Waterproofing Material Co. S.A.E

شركة النيل للمواد العازلة ش.م.م

50, Al Khalifa Al Maamoun St. Roxy - Heliopolis, Cairo - Egypt, Tel : (202) 24511194 - 24511195 Fax: (202) 24511198

Plant: ASPPC Industrial complex - Merghem - Alexandria

Web Site: www.bitunil.com

Email: bitunil@bitunil.com